

Vigor

Composition

Pile 85% Wool, 15% Nylon
Ground 100% Cotton

Weight

820g/m² ±5%

Width

150cm ±2% Usable

Breaking load

Warp: 400N min Weft: 700N min
(BS EN ISO 13934-1)

Extension at break

10% min (BS EN ISO 13934-1)

Burst strength

1000KN/m² min (BS EN ISO 13938-1)

Abrasion Resistance

60,000 Martindale cycles (BS EN ISO 12947)

Thickness

4.2±0.8mm (BS 4051)

Dimensional change (cold water immersion)

Warp: 3% max Weft: 2% max
(BS 4736, ISO 7771)

Flammability

BR 252 Appendix A
EEC Directive 95/28/EEC

Light Fastness

6 (BS EN 20105)

Fastness to Rubbing

Wet 4 Dry 4 (ISO 105 - X12 2002)

Acid Perspiration

Change in shade: 4/5 Staining: 4
(BS EN ISO 105 E4)

Alkali Perspiration

Change in shade: 4/5 Staining: 4
(BS EN ISO 105 E4)

Fastness to Water

Change in shade: 4/5 Staining: 4
(ISO 105 - E01)

Spotting (BS EN ISO 105)

E07 (water): 4/5 max
E05 (acid): 4/5 max
E06 (alkali): 4/5 max

Dry cleaning

Solvent: 4 max Fabric: 4 max
(BS EN ISO 105-D01)

Shampoo (BS 1006 UK-TB)

Shade change: 4 max
Staining wool: 4 max
Staining cotton: 4 max

Maintenance

Vacuum regularly. Wipe clean with a damp cloth or shampoo using proprietary upholstery shampoo.

Colour Matching

Batch to batch variations in shade may occur within commercial tolerances.