

ANALYTICAL RESULTS
FOR
WASHINGTON METRO AREA TRANSIT AUTHORITY

Prepared By:

Central Virginia Laboratories & Consultants, Inc.
3109 Odd Fellows Road
Lynchburg, Virginia 24501
(804) 847-2852

<u>CVLC #</u>	<u>Client ID</u>	<u>% Asbestos Fibers</u>	<u>% Other Fibers</u>	<u>% Non-Fibrous Material</u>
94-10510	Heat-01	Chrysotile 40 Amosite ND, <1 Crocidolite ND, <1 <u>Total 40</u>	Cellulose 30	30

Collection Information

<u>CVLC #</u>	<u>Client ID</u>	<u>Sample Date</u>	<u>Sample Time</u>
94-10510	Heat-01	10/31/94	0700 hours

ND = Not Detected, <1%

If the above samples are building materials regulated by EPA's NESHAP regulations (renovation/demolition), the results may be biased on the high side. You may opt to have samples with less than 10 percent asbestos re-analyzed by the reportedly more accurate point count procedure in the EPA Interim Method for the identification of Asbestos in Bulk Materials.

ANALYTICAL RESULTS
FOR
WASHINGTON METRO AREA TRANSIT AUTHORITY

Prepared By:

Central Virginia Laboratories & Consultants, Inc.
3109 Odd Fellows Road
Lynchburg, Virginia 24501
(804) 847-2852

<u>CVLC #</u>	<u>Client ID</u>	<u>% Asbestos Fibers</u>	<u>% Other Fibers</u>	<u>% Non-Fibrous Material</u>
94-10738	Heat-02	Chrysotile 5* Amosite ND,<1 Crocidolite ND,<1 <u>Total 5</u>	Cellulose 75	20

* IN WHITE LAYERS

<u>CVLC #</u>	<u>Client ID</u>	<u>% Asbestos Fibers</u>	<u>% Other Fibers</u>	<u>% Non-Fibrous Material</u>
94-10739	Heat-03	Chrysotile 25 Amosite ND,<1 Crocidolite ND,<1 <u>Total 25</u>	Cellulose 40 Fibrous Glass 15	20

<u>CVLC #</u>	<u>Client ID</u>	<u>% Asbestos Fibers</u>	<u>% Other Fibers</u>	<u>% Non-Fibrous Material</u>
94-10740	Heat-04	Chrysotile 50 Amosite ND,<1 Crocidolite ND,<1 <u>Total 50</u>	Cellulose 20 Fibrous Glass 5	25

ND = Not Detected, <1%

If the above samples are building materials regulated by EPA's NESHAP regulations (renovation/demolition), the results may be biased on the high side. You may opt to have samples with less than 10 percent asbestos re-analyzed by the reportedly more accurate point count procedure in the EPA Interim Method for the identification of Asbestos in Bulk Materials.

<u>CVLC #</u>	<u>Client ID</u>	<u>% Asbestos Fibers</u>	<u>% Other Fibers</u>	<u>% Non-Fibrous Material</u>
94-10741	Heat-05	Chrysotile 45 Amosite ND,<1 Crocidolite ND,<1 <i>Total</i> 45	Cellulose 30	25

Collection Information

<u>CVLC #</u>	<u>Client ID</u>	<u>Sample Date</u>	<u>Sample Time</u>
94-10738	Heat-02	11/03/94	0600 hours
94-10739	Heat-03	11/03/94	0605 hours
94-10740	Heat-04	11/03/94	0615 hours
94-10741	Heat-05	11/03/94	0630 hours

ND = Not Detected, <1%

If the above samples are building materials regulated by EPA's NESHAP regulations (renovation/demolition), the results may be biased on the high side. You may opt to have samples with less than 10 percent asbestos re-analyzed by the reportedly more accurate point count procedure in the EPA Interim Method for the identification of Asbestos in Bulk Materials.

CVLC CHAIN OF CUSTODY

Company Contact: CARLA GLAND

Company Name: WMA-TA

Address: 3101 EISENHOWER AVE
ALEXANDRIA, VA 22314

Phone Number: (202) 962-5077
Fax Number: (202) 962-5060

Project Number:	Project Name:
-----------------	---------------

Project Name: ROYAL STREET - BUS BAY

Samplers: (Signature/Print)

Carla Ogano / Carla A. Ogano

[illegible]Transported on ice: ☐ Yes ☒ No Temperature upon receipt: _____

Method of Transportation:	7868334526 115	P.O. No.
---------------------------	-------------------	----------

Relinquished by: (Signature/Print)

Date/Time

Relinquished/Received by: (Signature/Print)
Carla A. Gano

Date/Time

Received by CVLC:

Date/Time

Comments:

Bank Sample to be Analyzed for Assets
using Plan - Result

24-HR 7A-T

$$\frac{C}{C}$$

Central Virginia Laboratories & Consultants

3109 Odd Fellows Road
Lynchburg, Virginia 24501
Telephone (804) 847-2852 Fax: (804) 847-2850

Company Name: WMA-77A

Address: 3101 EISENHOWER AVE
ALEXANDRIA, VA 22314

Phone Number: (702) 942-5077 Fax Number: (702) 942-5000

Project Number:

Project Name:

Project Name: ROYAL STREET - CALAGE

Samplers: (Signature/Print)

Carla Q. Ingaño / Carla A. Glezvo

[illegible]Transported on ice: ☐ Yes ☒ No

Temperature upon receipt:

Method of Transportation: _____

Relinquished by: (Signature/Print)

Date/Time 11/2:04 07:00

Comments:	BULK SAMPLES TO BE ANALYZED FOR ASBESTOS USING PLM - <u>RUSH</u>
-----------	--

Relinquished/Received by: (Signature/Print)

Date/Time

Received by CVLC:

Date/Time

Central Virginia Laboratories & Consultants

3109 Odd Fellows Road
Lynchburg, Virginia 24501
Telephone (804) 847-2852 Fax: (804) 847-2830

$$\frac{\partial}{\partial t}$$

FIELD SAMPLE LOG

ROYAL ST

<u>No</u>	<u>Description</u>	<u>Location</u>	<u>Result</u>
ROYAL			
HEAT-01	Pipe ins, corr.	Bus barn	
HEAT-02	Pipe ins, wrap	2nd fl shop	
HEAT-03	Pipe ins, wrap	Adj to garage	
HEAT-04	Pipe fty (wrap pi)	2nd fl shop	
HEAT-05	Pipe ins, corr.	Small bldg	